

Polymist® F5A

polytetrafluoroethylene

Polymist® F5A a white PTFE micronized powder PTFE micronized powder composed of discrete particles.

Designed for use in critical engineering and high-end performance elastomers and coatings, Polymist® F5A will improve abrasion and tear resistance as well as non-stick properties, mar and abrasion resistance.

Polymist® F5A can also be used in plastics application to improve wear resistance and low coefficient of friction or in lubricants for its thickening effect, lubricity, improved corrosion and temperature resistance.

Main features of Polymist® F5A are:

- Improved lubricity, abrasion, scratch and rub resistance
- Increased (hot) tear strength
- Better flex life
- Increased slip and surface lubricity
- Reduced blocking
- Better chemical resistance
- Increased temperature resistance
- Gloss retention

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Uses	• Additive
Appearance	• White
Forms	• Powder

Physical

	Typical Value	Unit	Test method
Average Particle Size			Internal Method
D50	4.0	µm	
D99	15	µm	
Bulk Density	400	g/l	ASTM D4895
Specific Surface Area	3.0	m ² /g	Internal Method

Additional Information

	Typical Value	Unit	Test method
Grind in Oil	2.50		NPIRI
Melt Temperature	320 to 330	°C	ASTM D3418

Polymist® F5A

polytetrafluoroethylene

Processing

- Besides its main function as a wear additive, Polymist® F5A can be used at low concentration to improve mold release properties.
- Internal or open mixers (e.g. Banbury or two-roll mixers) are normally used to allow a good distribution of Polymist® F5A in the elastomeric compound. Additional fillers are normally included with Polymist micronized PTFE during the blending process. The resulting elastomeric composition can then be processed under normal conditions.
- Polymist® F5A can also be used as additives in paints and coatings where improvements in non-stick, mar resistance, slip, chemical resistance, and moisture repelling characteristics are desired. Polymist® F5A may be used independently as an additive or in combination with polyethylene waxes. The PTFE content at the surface layer is required in order to impart the properties of PTFE to the coating.

Storage and Handling

- The usual precautions for safe storage and handling of Polymist® F5A should be taken according to material safety documentation and experience. There will be no chemical deterioration of the Polymist® F5A during proper storage.
- Shelf life of Polymist® F5A micronized powders will vary depending upon whether the recommended storage conditions are maintained and whether the material remains free from foreign contamination during storage time (not exposed to dirt, dust, water or other chemicals). The material should remain sealed in the original containers and storage conditions should provide for protection from temperature extremes as well as rain, snow or other wet environments (or such conditions which may damage the storage containers in which the product is stored).

Safety and Toxicology

- Before using Polymist® F5A PTFE micronized powders, consult the product Material Safety Data Sheet and follow all label directions and handling precautions.
- As with all PTFE materials, handling and processing should only be carried out in well ventilated areas. Vapor extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help.
- Do not smoke in areas contaminated with powder, vapor or fumes.
- See Material Safety Data Sheet for detailed advice on waste disposal methods.

Packaging

- Polymist® F5A is packaged in 25 kg nonreturnable drums. Each drum has two bag liners made of polyethylene resin.
-

Notes

Typical properties: these are not to be construed as specifications.

Polymist® F5A

polytetrafluoroethylene

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2020 Solvay Specialty Polymers. All rights reserved.

